

## TECAPEEK CF30 black - 型材 (棒材, 板材, 管件)

### 化學命名

PEEK (聚醚醚酮)

### 顏色

黑色 不透明

### 密度

1.38 g/cm<sup>3</sup>

### 添加物

碳纖維

### 主要特色

- 良好的耐化學性
- 改良過的強度
- 固有的防火性
- 耐水解和熱蒸氣
- 極高的剛性
- 極高的耐蠕變性
- 良好的尺寸穩定性
- 高能輻射抗性

### 目標產業

- 機械工程
- 石油和天然氣工業
- 化學技術
- 汽車工業
- 航空與航太科技
- 真空科技

機械特性	參數	值	單位	標準	註解
抗拉強度	50mm/min	112	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
彈性模數 (張力測試)	1mm/min	6000	MPa	DIN EN ISO 527-2	(1) (2) For flexural test: support span 64mm, norm specimen.
斷裂伸長率	50mm/min	10	%	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
抗彎強度	2mm/min, 10 N	184	MPa	DIN EN ISO 178	(2) (4) For Charpy test: support span 64mm, norm specimen.
彈性模數 (彎曲測試)	2mm/min, 10 N	6100	MPa	DIN EN ISO 178	
壓縮強度	1% / 2% / 5% 5mm/min, 10 N	25/47/111	MPa	EN ISO 604	(3)
衝擊強度(Charpy)	max. 7.5J	92	kJ/m <sup>2</sup>	DIN EN ISO 179-1eU	(4)
蕭氏硬度	D	90		DIN EN ISO 868	
熱特性	參數	值	單位	標準	註解
玻璃轉化溫度		147	°C	DIN EN ISO 11357	(1)
熔化溫度		341	°C	DIN EN ISO 11357	(2)
使用溫度	short term	300	°C		(2)
使用溫度	long term	260	°C		
熱膨脹 (CLTE)	23-60°C, long.	4	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
熱膨脹 (CLTE)	23-100°C, long.	4	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
熱膨脹 (CLTE)	100-150°C, long.	6	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
比熱		1.2	J/(g*K)	ISO 22007-4:2008	
導熱係數		0.66	W/(K*m)	ISO 22007-4:2008	
電性特性	參數	值	單位	標準	註解
表面電阻		10 <sup>3</sup> - 10 <sup>12</sup>	Ω	DIN EN 61340-2-3	
體積電阻		10 <sup>3</sup> - 10 <sup>12</sup>	Ω*cm	DIN EN 61340-2-3	
其他特性	參數	值	單位	標準	註解
吸水率	24h / 96h (23°C)	0.02 / 0.03	%	DIN EN ISO 62	(1) (2) (3) (4)
耐熱水/鹼		+	-	-	(2)
耐候性		-	-	-	(3)
耐燃性(UL94)	corresponding to	V0		DIN IEC 60695-11-10;	(4)

→ TECAPEEK產品使用Victrex®PEEK 450或Solvay KetaSpire®製成

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com). Technical changes reserved.