

## TECANYL GF30 natural - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PPE (Polyphenylene ether )

### Colour

beige opaque

### Density

1.3 g/cm<sup>3</sup>

### Fillers

glass fibres

### Main features

- very high stiffness
- electrically insulating
- good weldable and bondable
- sensitive to stress cracking
- high strength
- high dimensional stability

### Target Industries

- electronics
- energy industry
- mechanical engineering
- automotive industry

| Mechanical properties                 | parameter                     | value            | unit                             | norm                 | comment                                                                                                                                                                                         |
|---------------------------------------|-------------------------------|------------------|----------------------------------|----------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Tensile strength                      | 50mm/min                      | 73               | MPa                              | DIN EN ISO 527-2     | (1) For tensile test: specimen type 1b                                                                                                                                                          |
| Modulus of elasticity (tensile test)  | 1mm/min                       | 4100             | MPa                              | DIN EN ISO 527-2     | (2) For flexural test: support span 64mm, norm specimen.                                                                                                                                        |
| Tensile strength at yield             | 50mm/min                      | 73               | MPa                              | DIN EN ISO 527-2     | (3) Specimen 10x10x10mm                                                                                                                                                                         |
| Elongation at yield (tensile test)    | 50mm/min                      | 5                | %                                | DIN EN ISO 527-2     | (4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.                                                                                                                          |
| Elongation at break (tensile test)    | 50mm/min                      | 5                | %                                | DIN EN ISO 527-2     | (5) For Charpy test: support span 64mm, norm specimen.                                                                                                                                          |
| Flexural strength                     | 2mm/min, 10 N                 | 116              | MPa                              | DIN EN ISO 178       |                                                                                                                                                                                                 |
| Modulus of elasticity (flexural test) | 2mm/min, 10 N                 | 3900             | MPa                              | DIN EN ISO 178       |                                                                                                                                                                                                 |
| Compression strength                  | 1% / 2% / 5%<br>5mm/min, 10 N | 23/41/91         | MPa                              | EN ISO 604           |                                                                                                                                                                                                 |
| Compression modulus                   | 5mm/min, 10 N                 | 3300             | MPa                              | EN ISO 604           |                                                                                                                                                                                                 |
| Impact strength (Charpy)              | max. 7,5J                     | 37               | kJ/m <sup>2</sup>                | DIN EN ISO 179-1eU   |                                                                                                                                                                                                 |
| Shore hardness                        | D                             | 88               |                                  | DIN EN ISO 868       |                                                                                                                                                                                                 |
| Thermal properties                    | parameter                     | value            | unit                             | norm                 | comment                                                                                                                                                                                         |
| Glass transition temperature          |                               | 150              | °C                               | DIN EN ISO 11357     | (1) Found in public sources.                                                                                                                                                                    |
| Melting temperature                   |                               | n.a.             | °C                               | DIN EN ISO 11357     | (2) n.a. = not applicable                                                                                                                                                                       |
| Service temperature                   | short term                    | 110              | °C                               |                      | (3) Found in public sources.                                                                                                                                                                    |
| Service temperature                   | long term                     | 85               | °C                               |                      | Individual testing regarding application conditions is mandatory.                                                                                                                               |
| Thermal expansion (CLTE)              | 23-60°C, long.                | 4                | 10 <sup>-5</sup> K <sup>-1</sup> | DIN EN ISO 11359-1;2 |                                                                                                                                                                                                 |
| Thermal expansion (CLTE)              | 23-100°C, long.               | 4                | 10 <sup>-5</sup> K <sup>-1</sup> | DIN EN ISO 11359-1;2 |                                                                                                                                                                                                 |
| Specific heat                         |                               | 1.2              | J/(g*K)                          | ISO 22007-4:2008     |                                                                                                                                                                                                 |
| Thermal conductivity                  |                               | 0.28             | W/(K*m)                          | ISO 22007-4:2008     |                                                                                                                                                                                                 |
| Electrical properties                 | parameter                     | value            | unit                             | norm                 | comment                                                                                                                                                                                         |
| surface resistivity                   |                               | 10 <sup>14</sup> | Ω                                | -                    |                                                                                                                                                                                                 |
| volume resistivity                    |                               | 10 <sup>14</sup> | Ω*cm                             | -                    |                                                                                                                                                                                                 |
| Other properties                      | parameter                     | value            | unit                             | norm                 | comment                                                                                                                                                                                         |
| Water absorption                      | 24h / 96h (23°C)              | 0.01 / 0.02      | %                                | DIN EN ISO 62        | (1) Ø ca. 50mm, h=13mm                                                                                                                                                                          |
| Resistance to hot water/ bases        |                               | (+)              | -                                | -                    | (2) (+) limited resistance                                                                                                                                                                      |
| Resistance to weathering              |                               | -                | -                                | -                    | (3) - poor resistance                                                                                                                                                                           |
| Flammability (UL94)                   | corresponding to              | HB               | -                                | DIN IEC 60695-11-10; | (4) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory. |

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com). Technical changes reserved.

Manufactured by: Ensinger Group,  
a German based plastic manufacturer

Represented by:  
Ensinger Asia Holding Pte Ltd.  
(Singapore Branch)  
for Asia Pacific other than Japan+China

63 Hillview Avenue #02-03  
Lam Soon Industrial Building  
Singapore 669569  
Tel +65 65524177  
Fax +65 65525177  
[www.ensingerplastics.com/en-sg/](http://www.ensingerplastics.com/en-sg/)

Date: 2023/07/19

Version: AD