

## TECAMID 66 LA natural - Halvfabrikata

### Kemisk betegnelse

PA 66 (Polyamid 66)

### Farve

elfenben uigennemsigtig

1.11 g/cm<sup>3</sup>

### Fillers

smøremiddel

### Vigtigste egenskaber

- gode glid- og slidegenskaber
- god kemisk resistens
- gode slidegenskaber
- resistent overfor mange olier, fedt og brændstoffer
- høj sejhed
- God svejse og klæbeevne

### Målsegmenter

- mekanisk industri
- Bilindustrien

Data genereret direkte efter bearbejdning (standard klima, Tyskland)

Mekaniske egenskaber	parameter	værdi	enhed	norm	kommentar
Trækstyrke	50mm/min	76	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
Elasticitetsmodul (tensile test)	1mm/min	3100	MPa	DIN EN ISO 527-2	1) (2) For flexural test: support span 64mm, norm specimen.
Trækforsøg -Forlængelse ved brud	50mm/min	76	MPa	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
Forlængelse ved brud	50mm/min	11	%	DIN EN ISO 527-2	(4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
Brudforlængelse	50mm/min	14	%	DIN EN ISO 527-2	(5) For Charpy test: support span 64mm, norm specimen.
Bøjningsstyrke	2mm/min, 10 N	102	MPa	DIN EN ISO 178	2) (6) Specimen in 4mm thickness
Elasticitetsmodul (flexural test)	2mm/min, 10 N	2800	MPa	DIN EN ISO 178	
Kompressionsstyrke	1% / 2% / 5% 5mm/min, 10 N	20/35/75	MPa	EN ISO 604	3)
Kompressionsmodul	5mm/min, 10 N	2400	MPa	EN ISO 604	4)
Slagstyrke (Charpy)	max. 7,5J	37	kJ/m <sup>2</sup>	DIN EN ISO 179-1eU	5)
Kugletrykshårdhed		145	MPa	ISO 2039-1	6)
Termiske egenskaber	parameter	værdi	enhed	norm	kommentar
Glasovergangstemperatur		54	°C	DIN EN ISO 11357	1) (1) Found in public sources.
Smeltetemperatur		261	°C	DIN EN ISO 11357	2) (2) Found in public sources.
Service temperatur	short term	120	°C		2) Individual testing regarding application conditions is mandatory.
Service temperatur	long term	90	°C		
Termisk udvidelse (CLTE)	23-60°C, long.	11	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Termisk udvidelse (CLTE)	23-100°C, long.	12	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Specifik varme		1.6	J/(g*K)	ISO 22007-4:2008	
Termisk ledeevne		0.36	W/(K*m)	ISO 22007-4:2008	
Elektriske egenskaber	parameter	værdi	enhed	norm	kommentar
Specifik overflademodstand		10 <sup>14</sup>	Ω	DIN IEC 60093	
Specifik volumen resistens		10 <sup>14</sup>	Ω*cm	DIN IEC 60093	
Andre egenskaber	parameter	værdi	enhed	norm	kommentar
Vandabsorption	24h / 96h (23°C)	0.2 / 0.4	%	DIN EN ISO 62	1) (1) Ø ca. 50mm, h=13mm
Resistens overfor hedt vand / baser		(+)		-	2) (2) (+) limited resistance
Resistens overfor vejrpåvirkning		-		-	3) (3) - poor resistance
Brandbarhed (UL94)	corresponding to	HB		DIN IEC 60695-11-10;	4) (4) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.