

TECATRON PVX black - Stock Shapes (rods, plates, tubes)

Chemical Designation

PPS (Polyphenylensulfide)

Colour

black opaque

Density

1.5 g/cm³

Fillers

carbon fibres, PTFE, graphite

Main features

- very good chemical resistance
- good heat deflection temperature
- very good slide and wear properties
- inherent flame retardant
- high dimensional stability
- high stiffness
- high creep resistance

Target Industries

- mechanical engineering
- oil and gas industry
- vacuum technology
- automotive industry
- aircraft and aerospace technology

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	50mm/min	53	MPa	DIN EN ISO 527-2	
Modulus of elasticity (tensile test)	1mm/min	4600	MPa	DIN EN ISO 527-2	1)
Tensile strength at yield	50mm/min	53	MPa	DIN EN ISO 527-2	
Elongation at yield (tensile test)	50mm/min	2	%	DIN EN ISO 527-2	
Elongation at break (tensile test)	50mm/min	2	%	DIN EN ISO 527-2	
Flexural strength	2mm/min, 10 N	91	MPa	DIN EN ISO 178	2)
Modulus of elasticity (flexural test)	2mm/min, 10 N	4800	MPa	DIN EN ISO 178	
Compression strength	1% / 2% / 5% 5mm/min, 10 N	19/36/89	MPa	EN ISO 604	3)
Compression modulus	5mm/min, 10 N	3300	MPa	EN ISO 604	4)
Impact strength (Charpy)	max. 7,5J	14	kJ/m ²	DIN EN ISO 179-1eU	5)
Shore hardness	D	85		DIN EN ISO 868	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		94	°C	DIN EN ISO 11357	1)
Melting temperature		281	°C	DIN EN ISO 11357	
Service temperature short term		260	°C		2)
Service temperature long term		230	°C		
Thermal expansion (CLTE)	23-60°C, long.	5	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-100°C, long.	6	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	100-150°C, long.	13	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Specific heat		0.9	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity		0.58	W/(K*m)	ISO 22007-4:2008	
Electrical properties	parameter	value	unit	norm	comment
surface resistivity		10 ⁴ -10 ¹⁰	Ω	DIN EN 61340-2-3	
volume resistivity		10 ⁷ -10 ¹²	Ω*cm	DIN EN 61340-2-3	
Other properties	parameter	value	unit	norm	comment
Water absorption	24h / 96h (23°C)	<0.01 / <0.01	%	DIN EN ISO 62	1)
Resistance to hot water/ bases		+	-		2)
Resistance to weathering		(+)	-		3)
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	4)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.