

TECAPET black - Stock Shapes (rods, plates, tubes)

Chemical Designation

PET (Polyethylene terephthalate)

Colour

black opaque

Density

1.39 g/cm³

Main features

- good chemical resistance
- very high strength
- easy to polish
- good weldable and bondable
- good slide and wear properties
- good machinability
- high toughness

Target Industries

- mechanical engineering
- automotive industry
- electronics
- food technology

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	50mm/min	91	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
Modulus of elasticity (tensile test)	1mm/min	3400	MPa	DIN EN ISO 527-2	(2) For flexural test: support span 64mm, norm specimen.
Tensile strength at yield	50mm/min	91	MPa	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
Elongation at yield (tensile test)	50mm/min	4	%	DIN EN ISO 527-2	(4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
Elongation at break (tensile test)	50mm/min	15	%	DIN EN ISO 527-2	(5) For Charpy test: support span 64mm, norm specimen.
Flexural strength	2mm/min, 10 N	134	MPa	DIN EN ISO 178	2)
Modulus of elasticity (flexural test)	2mm/min, 10 N	3400	MPa	DIN EN ISO 178	
Compression strength	1% / 2% / 5% 5mm/min, 10 N	19/36/86	MPa	EN ISO 604	3)
Compression modulus	5mm/min, 10 N	2800	MPa	EN ISO 604	4)
Impact strength (Charpy)	max. 7,5J	35	kJ/m ²	DIN EN ISO 179-1eU	5)
Shore hardness	D	85		DIN EN ISO 868	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		81	°C	DIN EN ISO 11357	1)
Melting temperature		244	°C	DIN EN ISO 11357	(1) Found in public sources.
Service temperature	short term	170	°C		(2) Found in public sources. Individual testing regarding application conditions is mandatory.
Service temperature	long term	110	°C		
Thermal expansion (CLTE)	23-60°C, long.	8	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-100°C, long.	10	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Electrical properties	parameter	value	unit	norm	comment
surface resistivity		10 ¹⁴	Ω	-	(1) Due to the black colourant and moisture uptake of the material the electrical insulation properties cannot be 100% guaranteed, despite single measurements suggesting otherwise.
volume resistivity		10 ¹⁴	Ω*cm	-	1)
Other properties	parameter	value	unit	norm	comment
Water absorption	24h / 96h (23°C)	0.02 / 0.03	%	DIN EN ISO 62	1)
Resistance to hot water/ bases		-		-	2)
Resistance to weathering		(+)		-	3)
Flammability (UL94)	corresponding to	HB		DIN IEC 60695-11-10;	4)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.

Manufactured by: Ensinger Group,
a German based plastic manufacturer

Represented by:
Ensinger Asia Holding Pte Ltd.
(Singapore Branch)
for Asia Pacific other than Japan+China

63 Hillview Avenue #02-03
Lam Soon Industrial Building
Singapore 669569
Tel +65 65524177
Fax +65 65525177
www.ensingerplastics.com/en-sg/

Date: 2023/07/19

Version: AE